

***KVD PL 4 K
BARUPLAST***

***KVD PL 4 K
BARUPLAST***

BARUPLAST KVD PL 4 K

50020

APP-modified bitumen membrane with polyester reinforcement

Top side: Light surface protection (Slate) with 8 cm selvedge (foil)
Bottom side: Foil

Intended use: Cap sheet of bituminous roofing systems
Standard: EN 13707

Technical data:

EN 1849-1	Mass per unit area	NPD
EN 1849-1	Thickness	4,2 (±0,2) mm
EN 13501-5	External fire exposure	NPD
EN 13501-1	Reaction to fire test	E
EN 1109	Flexibility at low temperatures	-10 °C
EN 1110	Flow resistance at elevated temperature	130 °C
EN 1931	Water vapour transmission	NPD

Packaging:18 rolls of 10 m x 1 m = 180 m² per pallet**BARUPLAST KVD PL 4 K**

50020

APP-modified bitumen membrane with polyester reinforcement

Top side: Light surface protection (Slate) with 8 cm selvedge (foil)
Bottom side: Foil

Intended use: Cap sheet of bituminous roofing systems
Standard: EN 13707

Technical data:

EN 1849-1	Mass per unit area	NPD
EN 1849-1	Thickness	4,2 (±0,2) mm
EN 13501-5	External fire exposure	NPD
EN 13501-1	Reaction to fire test	E
EN 1109	Flexibility at low temperatures	-10 °C
EN 1110	Flow resistance at elevated temperature	130 °C
EN 1931	Water vapour transmission	NPD

Packaging:18 rolls of 10 m x 1 m = 180 m² per pallet